



TECHNICAL DATA SHEET – CC 4000

Revised: 05/2018

PRODUCT DESCRIPTION

A 100% solids, high performance, high density, ceramic filled, brushable epoxy to seal and protect new or repaired surfaces from cavitation, erosion and wear.

FEATURES

- Medium viscosity achieve 100% contact with surface.
- Ideal for rebuilding worn areas less than 1/16" deep
- Excellent chemical resistance.
- Dry temperature resistance to 350°F.
- Low chloride content reduces the possibility of corrosion attack and stress cracking.

RECOMMENDED USES

- Protect pump casings, impeller blades, gate valves, water boxes and fan blades.
- Rebuild heat exchangers, tube sheets and other circulating water equipment.
- As a topcoat on repaired surfaces to provide an exceptionally smooth surface.
- As a prime coat prior to rebuilding with trowelable systems.
- As a touch-up & repair material for the Protec Series.

CHEMICAL RESISTANCE

Sodium Hypochlorite 5%	E	Sodium Hydroxide 50%	E
Trisodium Phosphate 5%	E	Aluminum Sulfate 5%	E
Sulfuric Acid 10%	E	Ferric Chloride	E
Sulfuric Acid 50%	E	Acetic Acid 10%	U
Hydrochloric Acid 10%	VG	Water	VG
Nitric Acid 10%	VG	Saturated salt solution	VG
Nitric Acid 40%	U	Leaded Gasoline	VG
Phosphoric Acid 10%	E	Mineral Spirits	VG
Phosphoric Acid 40%	VG	Propylene Glycol	VG
Sodium Hydroxide 10%	E	ASTM #3 oil	VG

E = Excellent VG = Very Good U = Unsatisfactory 7 day room temperature cure, 30 day immersion @ 75°F.

TYPICAL PROPERTIES

SOLIDS BY VOLUME	100%
VOLATILE ORGANIC COMPOUNDS	0.0 lb/gal (0 g/l)
THEORETICAL COVERAGE	1604 ft ² /gal @ 1 mil
RECOMMEND DFT (TYPICAL)	10-20 mils
NUMBER OF COATS	2 or more
MIX RATIO (BY VOLUME)	1 Hardener : 3.4 Resin
MIXED VISCOSITY	28000 cps
SHELF LIFE @ 60-90°F (16-32°C)	Part A 12 months Part B 12 months
TEMPERATURE RESISTANCE	350°F (dry)
COLOR	Blue

SPECIFICATION DATA

COMPRESSIVE STRENGTH - ASTM D 695	12000 psi
ABRASION RESISTANCE - ASTM D 4060 CS 17 WHEEL – 1000G/1000 CYCLES	15 mg loss
ADHESIVE TENSILE SHEAR - ASTM D 1002	2300 psi
CURED HARDNESS - ASTM D 2240	90 Shore D
DIELECTRIC STRENGTH - ASTM D 149	382 volts/mil

ORDERING INFORMATION

PACKAGING	1 gal kits
-----------	------------

CC 4000

(CERAMIC COAT 4000)
BRUSHABLE EPOXY CERAMIC COAT



SURFACE PREPARATION

Remove all oil, grease or other contaminants from the surface to be coated in accordance with SSPC-SP 1.

PREFERRED: Abrasive blast to a White Metal Blast in accordance with SSPC-SP 5 and obtain a 2-4 mil (50-100 μ) angular anchor pattern.

NOTE: For equipment that has been handling sea water or other salt solutions a test for chloride contamination should be performed prior to application. If chlorides are present at 40 ppm or greater the substrate shall be re-cleaned until the chlorides are less than 40 ppm.

MIXING

Material is formulated to be easily brush or roll onto prepared surfaces using a short bristle brush or roller. Add 1 part hardener to 3.4 parts resin and power mix thoroughly for about 4 minutes or until a uniform consistency is achieved, being careful to mix material from bottom and sides of the container. It is strongly recommended that only full kits be mixed. If less than full kits use the following ratio by volume: 1 part hardener to 3.4 parts resin.

THINNING

Thinning not required for brush application. For spray application maybe thinned up to 10% with MEK Thinner.

NOTE: The addition of thinner will inhibit cure, allow additional time between coats.

POT LIFE

MATERIAL TEMPERATURE	TIME
75°F (24°C)	45 minutes

APPLICATION CONDITIONS

	NORMAL	MINIMUM	MAXIMUM
MATERIAL	75-90°F (24-32°C)	55°F (13°C)	90°F (32°C)
SURFACE	75-90°F (24-32°C)	55°F (13°C)	90°F (32°C)
AMBIENT	75-90°F (24-32°C)	55°F (10°C)	90°F (32°C)
HUMIDITY	30-50%	0%	85%

Surface temperature must be 5°F (3°C) above the dew point.

APPLICATION

Brush / Roller: use a short bristle brush or roller in a minimum of 2 coats to achieved desired thickness.

AIRLESS:

PUMP RATIO	45:1 MIN	TIP SIZE	.018-.020"
MATERIAL HOSE*	3/8" ID min 100' max	TIP PRESSURE PSI	2500-2800

CURE TIME

These times are based on a 30-50% RH. Excessive film thickness, cooler temperatures or inadequate ventilation will require longer cure times and could result in premature failure.

SURFACE TEMPERATURE

	50°F	60°F	70°F	80°F	90°F	100°F
TACK FREE	9 hours	6 hours	3 hours	2 hours	1 hour	1 hour
RECOAT (MIN)	10 hours	5 hours	4 hours	3 hours	2 hours	1.5 hours
RECOAT (MAX)	38 hours	32 hours	20 hours	14 hours	10 hours	8 hours
FULL CURE LIGHT LOAD	56 hours	32 hours	20 hours	14 hours	10 hours	8 hours
NON-CHEMICAL SERVICE	4 days	48 hours	36 hours	24 hours	18 hours	12 hours
CHEMICAL IMMERSION	12 days	8 days	6 days	4 days	3 days	2 days

- If the material has exceeded its maximum recoat time or full cure time contact ITW Polymers Sealants North America, Inc. for recommended recoating procedures.
- Curing can be accelerated by using heat after the coating has been allowed to harden under ambient conditions. At 150°F material will cure in 4 hours.
- Holiday testing per NACE RP0199-98 should be conducted for all coatings going into immersion service. Use a setting of 100 volts/mil. All pinholes must be marked and repaired.

SAFETY INFORMATION

- Read the Safety Data Sheet (SDS) and container labels for detailed health and safety information.
- Do not apply material in enclosed areas without adequate air exchange and ventilation.
- All application personnel must use respirators rated for organic vapors, or in confined spaces wear fresh air respirators or fresh air hoods.
- Wear protective clothing, gloves and eye protection.
- Breathing fumes or contact with the skin may cause severe allergic reactions.

This product is intended for industrial use by properly trained professional applicators only.

STORAGE CONDITIONS

- Coatings need to be protected from moisture contamination.
- Store drums and pails in a dry location at 55-90°F (13-32°C).
- Materials **must** be kept above 55°F (13°C).
- Use MEK or similar solvent for clean-up.

ITW Polymers Sealants North America, Inc. warrants its products to be free from defects in material and workmanship. ITW Polymers Sealants North America, Inc.'s sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Polymers Sealants North America, Inc.'s option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Polymers Sealants North America, Inc. in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Polymers Sealants North America, Inc. of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW Polymers Sealants North America, Inc. makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Polymers Sealants North America, Inc. be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW Polymers Sealants North America, Inc., whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Polymers Sealants North America, Inc. cannot guarantee that color will conform to sample, if provided.