



TECHNICAL DATA SHEET – ULTRATHANE 5410

Revised: 05/2018

PRODUCT DESCRIPTION

A fast cure 100% solids hot spray applied coating system designed to produce a tough, impact resistant surface designed for a number of applications.

FEATURES

- No primer required onto EPS or PU foam.
- Fast cure for increased productivity
- Zero VOC's

RECOMMENDED USES

Often used as a protective coating for wood in speaker cabinet applications ensuring an easy clean long lasting finish.

PACKAGE SIZE

| | |
|--------|--|
| VOLUME | 10 & 110 US Gallons 37.8 & 415.8 Liters |
| WEIGHT | 39.9 & 438.7 kg |

PHYSICAL PROPERTIES

| | |
|---------------------------|--|
| COLOR | A Component is Amber ISOCYANATE B Component is Black POLYOL Mixed product is Black |
| MIX RATIO BY VOLUME A:B | 1:1 |
| MIX RATIO BY WEIGHT A:B | 1:1.13 |
| SG | 1:1 |
| % SOLIDS BY VOLUME | 100 |
| FLASH POINTS, °C | 149 |
| GEL TIME AT 60°C/ SECONDS | 5-10 |
| RECOMMENDED DFT, MM | ~0.75-1.50mm in one multi pass coat |

PERFORMANCE PROPERTIES

| | |
|---|------------------------------|
| TENSILE STRENGTH, MPA | 25-30 |
| ELONGATION, % | 20-30 |
| TEMPERATURE RESISTANCE, °C | Maximum 65 |
| THEORETICAL COVERAGE | 1.0 L/m ² /mm dft |
| HARDNESS, SHORE D | 70-75 |
| IMPACT RESISTANCE, KJ/M ² (ISO 180) | 31.5 |
| GARDNER IMPACT, M/KG (ASTM D2795) | 2.48 |

ULTRATHANE 5410



TECHNICAL DATA SHEET – ULTRATHANE 5410

ORDERING INFORMATION

| | |
|-----------------|---|
| PACKAGING | 1 gal kits (Includes Adhesion Promoter 1552) |
| SHIPPING WEIGHT | ~ 12 lbs (5.5 kg) |

SURFACE PREPARATION

All substrates should be clean, dry and free from any oil or grease. Metal should be abrasive blasted to produce an SA 2 ½ finish with a minimum of 75 micron profile for optimum adhesion. Product should only be applied in conditions where the Temperature is 3°C above the dew point and Relative Humidity is <85%

MIXING

The product is hot spray applied and mixing is an essential part of the operation occurring within the gun. (See Application section for further info)

APPLICATION

- Prior to commencing use of the product ensure that the two components are stored at temperature no lower than 20°C, a temperature of around 25°C is preferable and can be achieved by storage in a heated room or the use of electrical jacket heaters. The B component should be thoroughly power mixed prior to use.
- Suitable dispensing equipment is required in order to apply this product. Equipment must be capable of, delivering product to the gun at ~ 120-170 bar, with each component accurately metered in a 1:1 ratio by volume. The output of the machine should be capable of matching the highest output of the gun being used. Accurate temperature control of the two components should be possible, typically up to 70°C, with this heating being incorporated into the hose up to or as close as possible to the gun.
- The spray gun must use high pressure impingement to achieve satisfactory mixing of the components immediately on triggering. Some static mixer modified guns are also suitable, consult ITW Polymers Sealants North America to discuss suitable systems.
- To achieve an even finish during application the gun should be held at right angles to the substrate at a distance of 30-70cm, this can depend on the output volume and pressure.
- Review the appropriate Specification Guideline for detailed application instructions.

CURE TIME

| | 10°C | 20°C | 30°C |
|--------------------------------------|------|------|------|
| SURFACE DRY @ 1.0MM / MINUTES | 5 | 2 | 1 |
| CURE 100% @ 1.0MM / DAYS | 2 | 1 | 1 |
| RECOAT TIME MINIMUM / MINUTES | <8 | <4 | <2 |
| MAXIMUM WITHOUT REACTIVATION / HOURS | 15 | 8 | 1 |
| ABRADE, DEDUST / HOURS | >15 | >8 | >1 |

CLEAN UP

All equipment should be thoroughly cleaned directly after use using Mesamoll or suitable alternative. Spray guns should be cleaned using a proprietary cleaner as recommended by the manufacturer.

SHELF LIFE & STORAGE

12 months from date of shipment when stored at room temperature (~22°C) in original unopened containers in a dry environment.

PRECAUTIONS

For complete safety and handling information, please refer to Material Safety Data Sheets prior to using this product.

ITW Polymers Sealants North America, Inc. warrants its products to be free from defects in material and workmanship. ITW Polymers Sealants North America, Inc.'s sole obligation and Buyer's exclusive remedy in connection with the products shall be limited, at ITW Polymers Sealants North America, Inc.'s option, to either replacement of products not conforming to this warranty or credit to Buyer's account in the invoiced amount of the nonconforming products. Any claim under this Warranty must be made by Buyer to ITW Polymers Sealants North America, Inc. in writing within five days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life, or one year from the delivery date, whichever is earlier. Buyer's failure to notify ITW Polymers Sealants North America, Inc. of such nonconformance as required herein shall bar Buyer from recovery under this warranty.

ITW Polymers Sealants North America, Inc. makes no other warranties concerning this product. No other warranties, either expressed or implied, or statutory, such as warranties of merchantability or fitness for a particular purpose, shall apply. In no event shall ITW Polymers Sealants North America, Inc. be liable for consequential or incidental damages.

Any recommendation or suggestion relating to the use of the products made by ITW Polymers Sealants North America, Inc., whether in its technical literature, or in response to specific inquiry, or otherwise, is based on data believed to be reliable; however, the products and information are intended for use by Buyers having requisite skill and know-how in the industry, and therefore it is for the Buyer to satisfy itself of the suitability of the products for its own particular use, and it shall be deemed that Buyer has done so, at its sole discretion and risk. Variation in environment changes in procedures of use, or extrapolation of data may cause unsatisfactory results. ITW Polymers Sealants North America, Inc. cannot guarantee that color will conform to sample, if provided.

ITW POLYMERS SEALANTS NORTH AMERICA, INC.

111 S. Nursery Road, Irving, TX 75060 • Tel: +1 972-438-9111
Fax +1 972-554-3939 • info@itwsealants.com • futuracoatings.com

ITW Polymers Sealants North America